









airo-chemie
A. Schmiemann GmbH & Co. KG
chemisch-technische Produkte
D-40736 Langenfeld · Postfach 1143
D-40764 Langenfeld · Carl-Leverkus-Str. 27
Tel. (02173) 8538-0 · Fax 853860 + 853870

A2 1401 EN

Technical Data Sheet - Product Information

Product: SUPERFLEX



Characteristics:

Bright white 2c knifing filler based on polyester.
Extreme fineness, quick drying and excellent sanding.
Easy to apply, fast curing. Pinhole free surface after sanding.
Excellent adhesion on various bases especially on sheet steel, wood, chipboards and glass-fibre reinforced body parts based on polyester material.

Range of application:

Car-refinishing, furniture industry

Chemical basis:

SUPERFLEX: Unsaturated polyester resins, inert filling material, thixotropic agents and pigments.

Hardener: Benzoyl peroxide

Instructions for use:

Clean surface from rust and grease. Remove rust and lacquer coat.
Rough up surface with abrasive paper or sand blast.
Mix the required quantity of airo SUPERFLEX with approx. 2% of hardener paste and apply within 4-6 minutes.

Do not use on zinc-galvanized sheets, wash-primers and prime coats based on synthetic resins or nitro-cellulose undercoats.

Pot life:

With 2% hardener: 4-6 minutes
Excess of hardener does not accelerate the polymerisation rate but might cause loss of adhesion and/or discoloration of the following paint films.

Mixture:

100 parts: airo SUPERFLEX
2 parts: Hardener

Temperature conditions:

Material and surrounding temperature should range between +18 °C and +25 °C.
Do not apply at temperatures below +5 °C

Disposal consideration:

Dispose of according to local regulations.

Sanding:

Paper P 80 - 280

Storage stability:

12 months in tightly closed tins when kept at +20 °C.

Please consider our technical advice – be it verbally, in writing or testing and supplied to the best of our knowledge – as information only and without responsibility in respect to other parties. It does not release you from your obligation to test the products supplied regarding their suitability for the intended application. Handling and utilization of our products by the customer exceed our responsibility and are at the customer's liability. We guarantee that our products conform to their specification and we will refund or replace non conforming products only. Airo cannot be held responsible for any damages or accidents in connection with the use of our product.