



airo-chemie
A. Schmiemann GmbH & Co. KG
chemisch-technische Produkte
D-40736 Langenfeld · Postfach 1143
D-40764 Langenfeld · Carl-Leverkus-Str. 27
Tel. (02173) 8538-0 · Fax 853860 + 853870

CH 1401 EN


Technical Data Sheet - Product Information

Product: **MULTI**



Characteristics:

2c universal filler with a wide range of application.
Can be used as stopper and as a fine-putty.
Due to its high thixotropic quality typically used for application on vertical surfaces.
Little afterbake and easy sanding.
Excellent adhesion on various bases especially sheet steel, zinc-galvanised sheets, hot dip galvanised sheets, aluminium, wood and glass-fibre reinforced body parts based on polyester material.



Range of application:


Car-refinishing and industry



Chemical basis:

MULTI: Unsaturated polyester resins, inert filling material, thixotropic agents and pigments.

Hardener: Benzoyl peroxide




Instructions for use:

Clean surface from dirt and grease. Remove rust and lacquer.
Rough up surface with abrasive paper or sand blast.
Mix the required quantity airo MULTI with approx. 2% hardener paste and apply within 4-6 minutes
After a drying time of about 20 minutes the material is ready for sanding.




Do not use on wash-primers, prime coats based on synthetic resins or nitro-celulose undercoats.



Pot life:

With 2% hardener: 4-6 minutes


Excess of hardener does not accelerate the polymerisation rate but might cause loss of adhesion and/or discoloration of the following paint films.



Mixture:

100 parts: airo UNIPOL

2 parts: Hardener



Temperature:

Material and surrounding temperatures should range between +18 °C and +25 °C-.
Do not apply at temperatures below +5 °C

Disposal consideration:

Disposal according to local regulations.

Sanding:

Paper P 80 – 280

Please dry sand as polyester materials are sensitive to water

Storage stability:

12 months in tightly closed tins when kept at +20 °C.

Please consider our technical advice – be it verbally, in writing or testing and supplied to the best of our knowledge – as information only and without responsibility in respect to other parties. It does not release you from your obligation to test the products supplied regarding their suitability for the intended application. Handling and utilization of our products by the customer exceed our responsibility and are at the customer's liability. We guarantee that our products conform to their specification and we will refund or replace non conforming products only. Airo cannot be held responsible for any damages or accidents in connection with the use of our product.