








airo-chemie
A. Schmiemann GmbH & Co. KG
chemisch-technische Produkte
D-40736 Langenfeld · Postfach 1143
D-40764 Langenfeld · Carl-Leverkus-Str. 27
Tel. (02173) 8538-0 · Fax 853860 + 853870

F6 1401 EN

Technical Data Sheet - Product Information

Product: **LIGHT**



Characteristics:

2c polyester light weight putty for general filling works.
Low density of 1,3 g/cm³, easy to spread, good filling properties, no post-curing.
Easy sanding even after several days. The sanded surface is non-porous.
Excellent adhesion on various bases especially sheet steel, wood, chipboards and glass-fibre reinforced body parts based on polyester material.

Range of application:

Car-refinishing, industry, wood industry, orthopaedic industry

Chemical basis:

LIGHT: Unsaturated polyester resins, inert filling material, thixotropic agents pigments.
Hardener: Benzoyl peroxide

Instructions for use:

Clean surface from dirt and grease. Remove rust and old lacquer.
Rough up surface with abrasive paper or sand blast.
Mix airo LIGHT with approx. 2% hardener paste and apply within 4-6 minutes.

Do not use on galvanized or zinc-galvanized sheets, wash-primers, prime coats based on synthetic resins or nitro-cellulose undercoats.

Pot life:

4-6 minutes
Excess of hardener does not accelerate the polymerisation rate but might cause loss of adhesion and/or discoloration of the following paint films.

Mixture:

100 parts: airo LIGHT
2 parts: Hardener

Temperature conditions:

Material and surrounding temperatures should range between +18 °C and +25 °C.
Do not apply at temperatures below +5 °C

Disposal consideration:

Disposal according to local regulations.
Please dry-sand as polyester materials are sensitive to water.

Sanding:

Paper P 80 - 280

Storage stability:

6 months in tightly closed tins when kept at +20 °C.

Please consider our technical advice – be it verbally, in writing or testing and supplied to the best of our knowledge – as information only and without responsibility in respect to other parties. It does not release you from your obligation to test the products supplied regarding their suitability for the intended application. Handling and utilization of our products by the customer exceed our responsibility and are at the customer's liability. We guarantee that our products conform to their specification and we will refund or replace non conforming products only. Airo cannot be held responsible for any damages or accidents in connection with the use of our product.