



airo-chemie

A. Schmiemann GmbH & Co. KG
chemisch-technische Produkte
D-40736 Langenfeld · Postfach 1143
D-40764 Langenfeld · Carl-Leverkus-Str. 27
Tel. (02173) 8538-0 · Fax 853860 + 853870

H7 1401 EN

Technical Data Sheet - Product Information

Product: **STREICHSPACHTEL**




Characteristics:

2c polyester filler for brush application.

For all minor repair works and thin layers where the application of a spray filler is too complex.

Adhesion on various bases in particular sheet steel, wood, chipboards and glass-fibre reinforced polyester parts.



Range of application:


Car-refinishing and industrie



Chemical basis:

STREICHSPACHTEL: Unsaturated polyester resins, inert filling material, thixotropic agents, pigments.

Hardener: Benzoyl peroxide



Instructions for use:


Clean surface from dirt and grease. Remove rust and old lacquer.

Rough up surface with abrasive paper or sand blast.

Mix the required quantity of airo STREICHSPACHTEL with 2% hardener and apply within 5 - 8 minutes.




Do not use on wash-primer, prime coats based on synthetic resins or nitro-cellulose undercoats.



Pot life:


with 2% hardener: 5-8 minutes

Excess of hardener does not accelerate the polymerisation rate but might cause loss of adhesion and/or discoloration of the following paint films.



Mixture:

100 parts: airo STREICHSPACHTEL
2 parts: Hardener



Temperature conditions:

Material and surrounding temperatures should range between +18 °C and +25 °C.
Do not apply at temperatures below +15 °C

Disposal consideration:

Disposal according to local regulations.

Sanding:

Paper P 80 - 280

Storage stability:

12 months in tightly closed tins when kept at +20 °C.

Please consider our technical advice – be it verbally, in writing or testing and supplied to the best of our knowledge – as information only and without responsibility in respect to other parties. It does not release you from your obligation to test the products supplied regarding their suitability for the intended application. Handling and utilization of our products by the customer exceed our responsibility and are at the customer's liability. We guarantee that our products conform to their specification and we will refund or replace non conforming products only. Airo cannot be held responsible for any damages or accidents in connection with the use of our product