









airo-chemie
A. Schmiemann GmbH & Co. KG
chemisch-technische Produkte
D-40736 Langenfeld · Postfach 1143
D-40764 Langenfeld · Carl-Leverkus-Str. 27
Tel. (02173) 8538-0 · Fax 853860 + 853870

PU 1401 EN

Technical Data Sheet - Product Information

Product: 2K PU Spachtel



Characteristics:

Absolutely solvent free and virtually odourless 2c polyurethane filler.
Suitable for general indoor and outdoor filling works.
Easy and pinhole-free spreading.
Excellent adhesion on steel, aluminium, wood and glass fibre reinforced polyester objects.
Minimum shrinkage.

Range of application:

Nautic, car repair, metal processing works, carpentry, wood processing industry,
Model building, interior and exterior paintwork, orthopaedic works.

Chemical basis:

2c PU filler basis: OH-functional polymers
2c PU hardener: Polyisocyanates

Instructions for use:

Thoroughly clean the surface. Remove humidity, rust, dirt, grease and old paint.
Sand lightly. Mix the required quantity of 2c PU filler with the hardener at the ration 2:1
and apply within 5-10 minutes.

The hardener for the 2c PU filler is susceptible to humidity.
Therefore, it should be stored in tightly closed tins only.

Potlife:

of the 2:1 mixture: 5–10 minutes

Mixture:

100 parts: 2c PU filler base
50 parts: hardener

Temperature conditions:

The surrounding and material temperature should range between +18 °C und +25 °C.

Sanding:

After approx. 180 - 240 minutes with an orbital sanding machine (P80 – P240)
After approx. 180 - 240 minutes by hand (P80 – P120)

Disposal:

Disposal according to local regulations.

Storage stability:

6 months in tightly closed tins when stored at <25 °C

Please consider our technical advice – be it verbally, in writing or testing and supplied to the best of our knowledge – as information only and without responsibility in respect to other parties. It does not release you from your obligation to test the products supplied regarding their suitability for the intended application. Handling and utilization of our products by the customer exceed our responsibility and are at the customer's liability. We guarantee that our products conform to their specification and we will refund or replace non conforming products only. Airo cannot be held responsible for any damages or accidents in connection with the use of our product.